

	L #	Hits	Search Text	DBs	Time Stamp
1	L1	60565	(wet or steam or water) near15 (oxidiz\$3 oxidis\$3 oxidation)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:11
2	L8	271	(pyrogenic or pyrogenically) near15 (oxidiz\$3 oxidis\$3 oxidation)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:13
3	L15	8382	((hydrogen or "H.sub.2") near5 (oxygen or "O.sub.2")) near15 (oxidiz\$3 oxidis\$3 oxidation)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:50
4	L22	5	8 and (perovskite ferroelectric PZT BZT (tanatalum adj (pentaoxide pentoxide oxide)) (high adj dielectric)).ti,ab.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:14
5	L29	29	15 and (perovskite ferroelectric PZT BZT (tanatalum adj (pentaoxide pentoxide oxide)) (high adj dielectric)).ti,ab.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:52
6	L36	3123	1 and 15	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:50
7	L43	3123	1 and 15 and ((hydrogen or "H.sub.2") near5 (oxygen or "O.sub.2"))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 13:51
8	L50	7744	1 and ((hydrogen or "H.sub.2") near5 (oxygen or "O.sub.2"))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:06
9	L57	32	50 and (perovskite ferroelectric PZT BZT (tanatalum adj (pentaoxide pentoxide oxide)) (high adj dielectric)).ti,ab.	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:07
10	L64	831	RTO (rapid adj thermal adj (oxidation oxidiz\$3 oxidis\$3))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:06
11	L71	51	64 and ((hydrogen or "H.sub.2") near5 (oxygen or "O.sub.2"))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:06
12	L78	12	71 and (perovskite ferroelectric PZT BZT (tanatalum adj (pentaoxide pentoxide oxide)) (high adj dielectric))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:07
13	L85	15	8 and (perovskite ferroelectric PZT BZT (tanatalum adj (pentaoxide pentoxide oxide)) (high adj dielectric))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM TDB	2001/08/23 14:15